




















## CHROME PIGMENTS - TECHNICAL SPECIFICATIONS

<b>RAVESHIA COLOURS PVT. LTD.</b>  <b>PRODUCT</b>	<b>Product Code</b>	<b>MASS TONE</b>	<b>TINT TONE</b> <b>1:5 TiO<sub>2</sub></b>								<b>Bleeding Resistance (1-5 Scale)</b>			<b>Resistance to</b>			<b>Application</b>									
				<b>Colour Index</b>	<b>Oil Absorption</b>	<b>Moisture Content, %</b>	<b>Specific Gravity</b>	<b>Bulk Density Gms/CC</b>	<b>Residue on Sieve 320 Mesh</b>	<b>Water</b>	<b>Acid (HCL)</b>	<b>Alkali (NaOH)</b>	<b>5% Soap Solution</b>	<b>Light</b>			<b>Heat</b>			<b>Air Dry Enamel</b>	<b>Stoving Enamels</b>	<b>N.C. Lacquer</b>	<b>Offset / Letter press Ink</b>	<b>Liquid Links</b>	<b>Plastics</b>	<b>PVC Leather / Linoleum</b>
														<b>Light (1-8) Scale</b>	<b>Heat 180° C/30 mins</b>	<b>220° C/20 mins</b>	<b>250° C/10 mins</b>	<b>5</b>	<b>4</b>							
<b>Prime Rose Chrome</b> PY 34	101			77603	29	<1	5.6	0.98	0.5%	5	3	1	3	6	5	5	5	0	0	0	0	0	0	*	*	
<b>Lemon Chrome</b> PY 34	122			77603	26	<1	5.0	0.78	0.5%	5	3	3	3	6	5	5	4	0	0	0	0	0	0	0	0	
<b>Lemon Chrome</b> PY 34	120			77603	26	<1	5.0	0.78	0.5%	5	3	3	3	6	5	5	4	0	0	0	0	0	0	0	0	
<b>Middle Chrome</b> PY 34	138			77603	29	<1	5.5	0.8	0.5%	5	3	3	3	6-7	5	4	3	0	0	0	0	0	0	0	0	
<b>Middle Chrome</b> PY 34	130			77603	29	<1	5.5	0.8	0.5%	5	3	3	3	6-7	5	4	3	0	0	0	0	0	0	0	0	
<b>Middle Chrome</b> PY 34	132			77603	29	<1	5.5	0.8	0.5%	5	3	3	3	6-7	5	4	3	0	0	0	0	0	0	0	0	
<b>Scarlet Chrome</b> PR 104	475			77605	20	<1	6.5	1.0	0.5%	5	3	3	3	6-7	5	4	3	0	0	0	0	0	0	0	0	
<b>Scarlet Chrome</b> PR 104	470			77605	20	<1	6.5	1.0	0.5%	5	3	3	3	6-7	5	4	3	0	0	0	0	0	0	0	0	
<b>Scarlet Chrome (H.T.)</b> PR 104	493			77605	22	<1	5.9	0.9	0.5%	5	3	3	3	6-7	5	5	5	0	0	0	*	*	0	0		

**Bleeding Scale (1-5)**  
 5 - No Bleed  
 1 - Bleeding

**Light Fastness**  
 Scale 1-8 as per Blue Wool Scale

**Heat Resistance (1-5)**  
 1 - Colour Change  
 5 - No Colour Change

**Application**  
 0 - Application  
 \* - Limited Application  
 X - Not Application

No bleeding in Ethy Alcohol, Butyl Acetate, White Spirit, Xylene, M.E.K., Linseed Oil, DCO, DOP/DBP.

NOTE: The analysis values & datas are merely indication & given in good faith are not warranted.