

 <b>Raveshia Organics LLP</b>		Physical Properties						Application		
	Raveshia Product	C.I. Number	Specific Gravity	O.A.	Light Fastness	Weather Fastness Mass	Heat Stability Mass	Coatings	Plastics	Inks
	Pigment Yellow 1	11680	1.3	40	7	-	160°C	●	■	○
	Pigment Yellow 3	11710	1.4	35	7	-	160°C	●	■	○
	Pigment Yellow 12	21090	1.5	45	5-6	-	160°C	●	○	●
	Pigment Yellow 13	21100	1.5	45	6-7	-	200°C	■	●	●
	Pigment Yellow 14	21095	1.5	45	5	-	200°C	●	○	●
	Pigment Yellow 17	21105	1.3	55	7	-	230°C	○	●	●
	Pigment Yellow 62	13940	1.4	40	7	-	260°C	■	●	■
	Pigment Yellow 65	11740	1.4	45	7	4	150°C	●	■	■
	Pigment Yellow 74	11741	1.4	40	7	4	190°C	●	■	■
	Pigment Yellow 83	21108	1.4	52	7	4	220°C	●	●	●
	Pigment Yellow 168	13960	1.5	35	7	5	240°C	○	●	■
	Pigment Yellow 183	18792	1.7	55	7-8	-	300°C	○	●	■
	Pigment Yellow 191	18795	1.55	55	7-8	-	300°C	●	●	■
	Pigment Orange 13	21110	1.3	38	7	-	180°C	●	●	●
	Pigment Orange 34	21115	1.3	38	7	-	180°C	●	●	●
	Pigment Red 3	12120	1.5	45	6	-	160°C	●	■	■
	Pigment Red 4	12085	1.4]	46	6	-	160°C	●	■	■
	Pigment Red 48:2	15865:2	1.8	50	7	-	220°C	●	●	●
	Pigment Red 48:4	15865:4	1.9	45	7	-	200°C	●	■	■
	Pigment Red 53:1	15585:1	1.8	52	4-5	-	240°C	■	●	●
	Pigment Red 57:1	15850:1	1.5	58	6	-	240°C	●	○	●
	Pigment Red 63:1	15880:1	1.5	58	5	-	200°C	●	■	■
	Pigment Red 170	12475	1.4	50	7	4	250°C	●	●	●
	Pigment Red 184	71130	1.7	60	8	5	200°C	●	■	●

Note: The Analysis values and data are merely an indication

TDS & MSDS available on request - [sales@raveshia.com](mailto:sales@raveshia.com)



ISO 9001:2008  
(QMS Certified)

Recommended - ●

Limited - ○

Not Recommended - ■